



Ti75,Ti80 Titanium additive

1. Properties & Application:

- (1). Apply to the Ti element addition of aluminum and other alloys, replacing Al-Ti master alloys, have both gain-refining function of alloys.
- (2). Titanium content: 75% or 80%. Put directly into the molten metal at normal smelting temperature, melts quickly (<3 minutes), the Ti element recovery \geq 90%.

2. Operation Technology Suggestion:

- (1). Temperature: 720~760°C
- (2). Dosage: According to calculating and experimental results..
- (3). Method: Skim off the dross and plunge Ti75 into the molten metal, stir the melt to homogenate after the l reaction finish, keep the molten metal static for 30~60 minutes.

3. Package and Storage:

Appearance: Dull gray tablet.

250g/tablet, 20kg/carton.

Keep dry and ventilated.

4. Period of validity:

Six months.